



B.P.C

BORZOUYEH SOIL MECHANIC & TECHNICAL LABORATORY

GROUT & MORTAR COMPRESSIVE & FLEXURAL STRENGTH REPORT

PROJECT: 4<sup>TH</sup> AROMATIC

LAB-GR-MO-101  
REPORT NO.:  
DATE: 04/05/2003


TEST METHOD : ASTM C579 - ASTM C580

OWNER: B.P.C

CONTRACTOR: J.K.T

SAMPLE NO.	DATE MADE	DENSITY ton/m <sup>3</sup>	GROUT TYPE			DATE TEST	COMPRESSIVE STRENGTH Kg/cm <sup>2</sup>			FLEXURAL STRENGTH Kg/cm <sup>2</sup>			LOCATION
			CEMENT BASE	CEMENT BASE NON SHRINK	EPOXY RESIN		3day	7day	28day	3day	7day	28day	
41/A	01/05/2003	2.21		RENDEROC		04/05/2003	279	342	504				ملاک نرمینس FOCROC
41/B		2.21		TG			325	346	483				
			نسبت آب به مصالح 0.15										

TESTED BY:



SUPERVISOR: