



Conbextra UW*

Non shrink cementitious grout for underwater installations

Uses

Conbextra UW is used for free flow or pumped grouting applications underwater or in tidal zones. There will be no significant 'wash-out' of the cement phase.

Applications include bridge columns, quay pillars, concrete piling, slipways and dams.

Advantages

- No risk of significant 'wash-out' of cement phase when placed underwater
- Displaces water effectively
- Gaseous expansion system compensates for shrinkage and settlement in the plastic state
- High early and ultimate strength and exceptional resistance to freeze-thaw cycling ensure durability of the hardened grout
- Chloride free
- Pre-packaged needing only on-site addition of water

Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Properties

The following results were obtained at a water:powder ratio of 0.22 at 20°C.

Compressive strength (BS 4550, Part 3:1978)	
1 day	: 25 N/mm ²
3 days	: 38 N/mm ²
7 days	: 44 N/mm ²
28 days	: 53 N/mm ²
Setting time (BS 5075, Part 1:1982)	
Initial	: 4.5 hours
Final	: 5.5 hours
Density of hardened grout : 2050 kg/m ³	
Expansion characteristics	: Controlled expansion occurs in unset material to ensure that the grout, when cured, will continue to occupy its original volume within the confines of the void in which it was placed.

Description

Conbextra UW is supplied as a ready to use powder. The addition of a controlled amount of clean water produces a free flowing grout.

The grout exhibits exceptional resistance to 'washing-out' of the cement phase when placed in stationary or moving water.

Conbextra UW is a blend of cement, graded fine aggregate and chemical additives which impart controlled expansion, water reduction and non 'wash-out' characteristics.

The aggregate grading minimizes segregation & bleeding whilst assisting flow characteristics.

Application instructions

Preparation

The substrate surface must be free from oil, grease or any loosely adherent material. If the concrete surface is defective or has laitance, it must be cut to a sound base.

Substrates which are permanently immersed should be sand-blasted or cleaned with a high pressure water jet. Non-immersed or intermittently immersed substrates can be prepared using these techniques.

Alternatively scabbling or bush hammering may be appropriate.

Formwork

The formwork should be constructed to be leakproof, as Conbextra UW is a free flowing grout, using foam rubber strip or mastic sealant beneath the formwork and between joints. Coat all formwork with Reebol*↑ to enable easy formwork release.

Mixing and placing

Mixing

For best results a mechanically powered grout mixer should be used. It is essential that machine mixing capacity and labour availability is adequate to enable the grouting operation to be carried out continuously.

This may require the use of a holding tank with provision for gentle agitation to maintain fluidity.

Measure accurately 4.4 litres of water for each 20 kg bag into the mixer. Slowly add the Conbextra UW whilst mixing continuously.

When all the powder is added mix continuously for 5 minutes ensuring a smooth even consistency is obtained. (Fluidity will increase with increased mixing.)

Conbextra UW*

Placing

Place the grout within 20 minutes of mixing to gain the full benefit of the expansion process. Continuous grout flow is essential. The mixed grout should be poured or pumped through a flexible tube, having a minimum diameter of 50 mm, to the lowest point in the form.

Care must be taken at the start of the grouting operation to restrict the grout flow so that water is not entrapped. The tube may be raised as necessary to reduce any back pressure. It should not be raised above the surface level of the grout.

Conbextra UW can be placed in thicknesses up to 75 mm in one pour when used above water.

When used underwater, the heat sink effect in this environment will allow thicknesses of up to 150 mm to be placed.

For thicker sections, up to 200 mm above water and 400 mm underwater, it is necessary to fill out Conbextra UW using a clean rounded well graded aggregate ranging from 2 to 10 mm.

The ratio of aggregate added to Conbextra UW should not exceed 1:1 by weight. For such mixes a concrete mixer should be used. Unrestrained surface area should be kept to a minimum.

Curing

Curing will not be required in intermittently or totally submerged situations. However, when cast above water, exposed areas should be thoroughly cured with Concure curing membrane, continuous application of water and/or wet hessian.

Cleaning

Because of its water resisting properties, equipment used for Conbextra UW will be difficult to clean. The use of hot water for cleaning purposes will assist.

Cured material can be removed mechanically or with Fosroc Acid Etch.

Limitations

- Conbextra UW must not be applied below 5°C



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service.

Fars Iran Limited

No. 9, 25 th St., Khaled Eslamboli
(Vozara) Ave., Tehran 15139 - Iran

telephone:
+98 (21) 88719021

fax:
+98 (21) 88721664

email:
iran@fosroc.com

www.fosroc.com



Estimating

Supply

Conbextra UW : 20 kg bags

Yield

Conbextra UW : Approximately 11.6 litres when mixed with 4.4 litres of water

Note: Allowance should be made for wastage when estimating quantities required.

Storage

Conbextra UW has a shelf life of 12 months if kept in a dry store in sealed bags.

If stored in high temperature and high humidity locations, the shelf life may be reduced.

Precautions

Health and safety

Conbextra UW contains cement powders which, when mixed or become damp, release alkalis which can be harmful to the skin. During use, avoid inhalation of dust and contact with skin and eyes.

Wear suitable protective clothing, gloves, eye protection and respiratory protective equipment.

The use of barrier creams provides additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water.

In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately — do not induce vomiting.

Fire

Conbextra UW is non-flammable.

* Denotes the trademark of Fosroc International Ltd.

↑ See separate data sheet