



# Nitoflor SL3000\*

Flow applied, 3 mm thick epoxy resin based floor topping

## Uses

Nitoflor SL3000 is designed for use in a wide range of light to medium industrial environments where a lasting solution to floor maintenance problems is required.

It provides a dense, impervious, coloured and chemically resistant floor surface which is hygienic and easy to clean. Typical applications include:

- plant rooms
- clean rooms
- light industrial plants
- production areas

## Advantages

- **Fast application** - minimizes downtime
- **Chemically resistant** - good resistance to a wide range of industrial chemicals
- **Durable** - good abrasion resistance
- **Hygienic** - provides a dense, impervious seamless floor surface which is easily cleaned
- **Attractive** - available in a wide range of colours to enhance the working environment

## Specification

Flow applied epoxy floor topping

The designated floor area shall be surfaced with Nitoflor SL3000, a 3 mm thick flow-applied epoxy resin floor topping.

The topping shall achieve a compressive strength of 60 N/mm<sup>2</sup> and a flexural strength of 30 N/mm<sup>2</sup> at 7 days when tested to BS 6319.

At 20°C, it shall be capable of accepting foot traffic at 24 hours and vehicular traffic at 48 hours.

## Description

Nitoflor SL3000 consists of graded aggregates bound in a pigmented epoxy resin binder.

It is supplied as a four component system, pre-weighed for on-site mixing.

When laid it provides a smooth, light reflective surface. It is available in a range of standard colours.

## Properties

The values given below are average figures achieved in laboratory tests. Actual values obtained on site may show minor variations from those quoted.

Pot life	@ 25°C	@ 35°C
<b>Nitoflor SL3000</b>	: 1 hour	20 minutes
<b>Nitoprime 25IR</b>	: 3 - 4 hours	1 - 1.5 hours
<b>Nitoprime 31</b>	: 1.5 - 2 hours	30 - 60 minutes
<b>Nitocote Primer Sealer</b>	: 2 hours	1 hour
Cure time		
<b>Food traffic</b>	: 24 hours	16 hours
<b>Vehicular traffic</b>	: 48 hours	36 hours
<b>Chemical resistance</b>	: 7 days	4 days

## Physical Properties

<b>Compressive strength @ 7 days (BS 6319, Part2)</b>	: 56 N/mm <sup>2</sup>
<b>Flexural strength @ 7 days (BS 6319, Part 3)</b>	: 35 N/mm <sup>2</sup>
<b>Tensile strength @ 7 days (BS 6319, Part 7)</b>	: 18 N/mm <sup>2</sup>
<b>Pull off strength @ 7 days cure (BS 1881, Part 207)</b>	: 4 N/mm <sup>2</sup> (Failure within the concrete substrate)
<b>Water absorption</b>	: Nil (ASTM C413)

## Chemical properties

Nitoflor SL3000 has excellent resistance at ambient temperatures to a wide range of industrial chemicals. Specific data is available on request. Note that it is especially important that spillage is cleaned up quickly and not allowed to dry since much higher concentrations of chemicals may occur on evaporation.

## Design criteria

Nitoflor SL3000 is designed for application at a nominal thickness of 3 mm. Substrates should be dry and not suffer, or be likely to suffer, from rising damp. If necessary, suitable damp-proof membranes should be installed to prevent this. Substrates should not have a relative humidity greater than 75% at the time of installation.

## Instructions for use

Nitoflor SL3000 should be applied by specialist contractors who must follow the procedures laid down in the Product Method Statement.

Fosroc works with a network of such applicators who have been trained in the correct installation procedures. The following steps are involved in the application which would normally take place over a 2 - 3 day period.

# Nitoflor SL3000\*

---

## Surface preparation

It is essential that Nitoflor SL3000 is applied to sound, clean and dry surfaces in order that maximum bond strength is achieved between the substrate and the flooring system. All dust and debris should be removed prior to application of the product or its primer.

### *New concrete floors*

New concrete, or cementitious substrates, should be at least 28 days old and have a moisture content not exceeding 5%. Laitance deposits on new concrete are best removed by light grit blasting, mechanical scabbling or grinding.

### *Old concrete floors*

Existing concrete floors which require refurbishment must be prepared to ensure a strong adhesive bond between flooring system & existing floor. Mechanical cleaning methods are strongly recommended particularly where heavy contamination by oil & grease has occurred or existing coatings are present. To ensure adhesion, all contamination should be removed. Proprietary chemical degreaser may be used on small areas of light contamination only.

### *Steel surfaces*

Steel surfaces should be degreased and grit blasted to SA2½ immediately prior to application. The prepared surface should then be primed with one coat of Nitocote Primer Sealer.

## Priming

All surfaces treated with Nitoflor SL3000 should be primed with Nitoprime 25IR, a solvent based epoxy resin primer designed for maximum absorption and adhesion to concrete substrates. Add the entire contents of the hardener tin to the base tin and mix the two primer components thoroughly for at least 2 minutes - under no circumstances should part mixing be considered. Once mixed, the primer should be applied immediately to the prepared substrate using stiff brushes and/or rollers. The primer should be well 'scrubbed' into the substrate to ensure full coverage, but care should be taken to avoid over unsightly application or 'ponding'. Allow the primer to dry (see table below) before proceeding to the next stage. Do not proceed whilst the primer is 'tacky' as this will lead to unsightly marks in the finished surface. Porous substrates may require a second primer coat – when the first coat is directly absorbed into the substrate – but minimum overcoating times must still be observed (see table below). The minimum overcoating times will vary slightly according to the porosity of the substrate. However, they should be in accordance with the following ambient application temperatures:

@ 20°C	:	8 - 12 hours
@ 30°C	:	6 - 8 hours
@ 40°C	:	4 - 6 hours

## Mixing

Nitoflor SL flooring is supplied in four pre-weighed packs (base, hardener, aggregate and colour pack) which are ready for immediate on-site use.

Part mixing of these components is not acceptable and will affect both performance and appearance of the finished floor, and would furthermore automatically invalidate Fosroc's standard product guarantee.

Mixing should be carried out using either a forced action mixer; or a heavy duty, slow-speed drill with proprietary mixing paddle attachment. All such equipment should be of a type and capacity approved by Fosroc.

The components should be mixed in a suitably sized mixing vessel. The colour pack should be added to the base container and mixed for 15 - 30 seconds, until homogeneous.

Then add the hardener and mix for further 30 seconds, until an even colour and texture is obtained. Thereafter, the contents of the graded aggregate pack should be slowly added and mixing carried out for a further 3 minutes until a completely homogenous material is obtained.

## Application

The applicator should ensure that there are sufficient supplies of plant, labour and materials to make the mixing and subsequent application process a continuous one for any given, independent floor area.

Once mixed, the material must be used within its specified pot life - see "Properties" section. The material should be poured onto the prepared and primed substrate as soon as mixing is complete.

It should be spread to the required thickness preferably using a pin screed, if not a serrated trowel; with care taken not to overwork the resin, spreading evenly and slowly. Immediately after laying, the material should be rolled, using a spiked nylon roller, to remove slight trowel marks, and to assist air release.

The rolling should be carried out using a 'back and forth' technique along the same path. An overlap of 50% with adjacent paths is recommended. The rolling process should continue for a minimum of 5 times on the same path, but should be prior to setting of the product.

## Floor Joints

All existing expansion or movement joints should be followed through the new floor surface. Joint sealant & joint geometry should be compatible with the floor type used, intended exposure conditions and likely movement characteristics of the substrate - consult the local Fosroc office for more details.



# Nitoflor SL3000\*

## Cleaning

Nitoprime 25IR, Nitocote Primer Sealer and Nitoflor SL3000 should be removed from tools and equipment with Fosroc Solvent 102 immediately after use. Hardened material can only be removed mechanically.

## Maintenance

The service life of a floor can be considerably extended by good housekeeping. Regular cleaning may be carried out using a rotary scrubbing machine with a water miscible cleaning agent at temperatures up to 50°C.

## Limitations

- Nitoflor SL3000 should not be applied on to surfaces known to, or likely to suffer from, rising dampness, potential osmosis problems or have a relative humidity greater than 75% as measured in accordance with BS 8203 Appendix A, or by a Hammond concrete/mortar moisture tester type COCO
- In areas where significant thermal shock is likely to occur, please consult the local Fosroc office
- Nitoflor SL3000 should not be applied to asphalt, weak or friable concrete, unmodified sand/cement screeds, PVC tiles or sheet. For information on other substrates, consult the local Fosroc office.
- Nitoflor SL3000 should not be installed at temperatures below 10°C or above 45°C
- In common with all epoxy materials some light shade changes may be experienced over the long term when placed in adverse conditions. Any such change in shade is not regarded as being detrimental to performance.

## Estimating

### Supply

<b>Nitoflor SL3000</b>	:	15 litre packs (Including colour packs)
<b>Nitoprime 25IR</b>	:	1 & 3 kg packs
<b>Nitocote Primer Sealer</b>	:	1 & 4 litre packs
<b>Fosroc Solvent 102</b>	:	4 & 20 litre cans

### Coverage

<b>Nitoflor SL3000</b>	:	5.0 m <sup>2</sup> /pack @ 3 mm thickness
<b>Nitoprime 25IR</b>	:	3.5 - 4.3 m <sup>2</sup> /kg
<b>Nitocote Primer Sealer</b>	:	4.0 - 5.0 m <sup>2</sup> /litre

**Note:** The coverage figures given are theoretical – due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced. Typically, an additional 10% should be allowed for surface irregularities and wastage although this will vary with site conditions.

## Storage

Nitoflor SL3000 has a shelf life of 12 months if kept in warehouse conditions at 30°C in the original, unopened pack.

Store in dry conditions between 5°C and 30°C, away from sources of heat & naked flames, in the original, unopened packs.

If stored at high temperatures the shelf life will be reduced.

## Precautions

### Health and safety

Nitoflor SL3000, Nitoprime 25IR, Nitocote Primer Sealer and Fosroc Solvent 102 should not come in contact with the skin and eyes, or be swallowed.

Ensure adequate ventilation and avoid inhalation of vapours.

Some people are sensitive to resins, hardeners and solvents. Wear suitable protective clothing, gloves and eye protection.

In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent.

In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice.

If swallowed seek medical attention immediately - do not induce vomiting.

### Fire

Nitoprime 25IR and Fosroc Solvent 102 are flammable. Keep away from sources of ignition. No smoking. In the event of fire extinguish with CO<sub>2</sub> or foam. Do not use a water jet. Nitoflor SL3000 and Nitocote Primer Sealer are nonflammable.

### Flash points

<b>Nitoprime 25IR</b>	:	39°C
<b>Fosroc Solvent 102</b>	:	33°C

### Disposal

Spillages of component products should be absorbed on to earth, sand or other inert material and transferred to a suitable vessel.

Disposal of such spillages or empty packaging should be in accordance with local waste disposal regulations. For further information, refer to the Product Material Safety Data Sheet.



# Nitoflor SL3000\*

---

## The Right Chemistry for Construction

Fosroc is one of the world's major manufacturers of advanced technology chemical based products for the construction and refurbishment industries. It operates internationally through a network of operating companies, licensees, distributors and agents.

Having over 70 years experience and using global resources for research and technical development, Fosroc has built a substantial worldwide reputation in manufacturing the most comprehensive range of high performance construction chemicals:

- Concrete admixtures
- Surface treatments
- Grouts and anchors
- Concrete repair
- Industrial flooring
- Protective coatings
- Joint sealants
- Waterproofing
- Adhesives
- F.R.P Structural Strengthening
- Specific building products

\* Denotes the trademark of Fosroc International Ltd.



### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service.

---

## Fars Iran Limited

No. 9, 25 th St., Khaled Eslamboli  
(Vozara) Ave., Tehran 15139 - Iran

**telephone:**  
+98 (21) 88719021

**fax:**  
+98 (21) 88721664

**email:**  
iran@fosroc.com

[www.fosroc.com](http://www.fosroc.com)

