

Nitoflor TF5000*

Heavy duty 5 mm thick, chemical and abrasion resistant epoxy floor screed

Uses

Nitoflor TF5000 provides an extremely high strength floor topping with exceptional resistance to attack from mechanical wear and chemical spillage. In addition to being impervious its use facilitates a safe non-slip finish for personnel and vehicular traffic, and is ideally suited for:

- Heavy engineering plants and steelworks
- Electricity substations and battery rooms
- Chemical handling and process areas
- Oil refineries and plating factories
- Dairies and soft drinks factories

In areas where high degrees of cleanliness are required, the surface of Nitoflor TF5000 can be sealed with either Nitoflor FC130*↑ or Nitoflor FC140*↑ epoxy resin floor coatings.

Advantages

- Long service life - exceptional resistance to abrasion and a wide range of chemicals
- Safe working environment - good gripping surface to both vehicular and pedestrian traffic
- Minimal disruption – 5 mm thickness causes little interference with existing levels
- Established track record - successfully proven in a wide variety of aggressive locations
- Versatile application - food grade and other special versions available to match individual requirements

Standards compliance

Tested to variety of international standards: ASTM C109-90 for compressive strength, BS 6319 for tensile and flexural strength and ASTM C501 for abrasion resistance.



Specification

The epoxy resin floor screed shall be Nitoflor TF5000 from Fosroc. The screed shall be 5 mm thick with a compressive strength of 85 N/mm², a flexural strength of 28 N/mm², and a tensile strength of 16 N/mm². The screed shall provide abrasion resistance in accordance with ASTM C501, having a maximum weight loss of 0.77 mg/1000 cycles.

Description

Nitoflor TF5000 is a solvent-free combination of epoxy resin, modified amine hardener, filled with specially graded inert aggregates. It is supplied in pre-weighed units of four part system including colour pack, which are ready for on-site mixing and application.

Nitoflor TF5000 is laid by trowel as a durable, chemically resistant screed approximately 5 mm thick. The complete system also includes Nitoprime 25IR*, a two-pack epoxy resin primer. The finished, cured floor has a slightly granular texture.

Technical support

Fosroc offers a comprehensive range of high performance, high quality repair, maintenance and construction products. In addition, Fosroc offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance in locations all over the world.

Properties

Mechanical characteristics

Compressive strength (ASTM C109:90)	:	85 N/mm ²
Flexural strength (BS 6319, Part 3)	:	28 N/mm ²
Tensile strength (BS 6319, Part 7)	:	16 N/mm ²
Abrasion resistance (ASTM C501)	:	0.77 mg/1000 cycles
Bond of strength to the concrete	:	> Cohesion strength of the concrete
Indentation characteristics Modified US MIL-D-3134	:	No indentation from a height of 2.4 m
Curing characteristics	@ 20°C	@ 30°C
Nitoflor TF5000		
Pot life	:	45 minutes 30 minutes
Initial hardness	:	18 hours 16 hours
Full cure	:	7 days 5 days
Nitoprime 25IR		
Pot life	:	45 minutes 20 minutes
Maximum overlay time	:	3 hours 90 minutes

Nitoflor TF5000*

Chemical resistance

Fully cured blocks of Nitoflor TF5000 have been tested in a wide range of aggressive chemicals commonly found in industrial environments. Tests were performed by constant immersion over a set period, followed by visual inspection and testing for Shore D hardness.

Acids (m/v)		
Hydrochloric acid 36%	:	Resistant
Sulphuric acid 10%	:	Resistant
Phosphoric acid 50%	:	Resistant
Nitric acid 30%	:	Resistant
Lactic acid 22.5%	:	Resistant
Citric acid 80%	:	Resistant
Alkalis (m/v)		
Sodium hydroxide 24%	:	Resistant
Ammonia 35%	:	Resistant
Solvents & organics		
Butanol	:	Resistant
White spirit	:	Resistant
Oil/grease/petrol	:	Resistant
Xylene	:	Resistant
Aqueous solutions		
Bleach	:	Resistant
Saturated sugar	:	Resistant
Saturated urea 10%	:	Resistant

All above properties have been determined by laboratory controlled tests and are in excess of those expected in practice. Nevertheless, success in use will be determined by the implementation of good housekeeping practices.

Instructions for use

Surface Preparation

It is essential that Nitoflor TF5000 is applied to sound, clean and dry surfaces in order that maximum bond strength is achieved between the substrate and the flooring system. All dust and debris should be removed prior to application of the product or its primer.

New concrete floors

Should be at least 21 days old (at 20°C) with maximum moisture content not exceeding 5%. Laitance deposits on new concrete floors are best removed by light grit blasting, mechanical scabbling or grinding.

Old concrete floors

Again, mechanical cleaning methods are strongly recommended on old concrete floors particularly where heavy contamination by oil and grease has occurred or existing coatings are present. These may well have been absorbed several millimetres into the concrete. To ensure adhesion, all contamination should be removed. Proprietary chemical degreaser may be used on small areas of light contamination only.

Steel surfaces

Steel surfaces should be degreased and grit blasted to SA2½ immediately prior to application.

Priming

All surfaces treated with Nitoflor TF5000 should be primed with Nitoprime 25IR, a solvent based epoxy resin primer designed for maximum absorption and adhesion to concrete substrates. Add the entire contents of the smaller hardener tin to the base tin and mix thoroughly. Once mixed, immediately apply the primer in a thin continuous film to the clean prepared surfaces. Work the primer into the surface and avoid over application and puddling. On porous floors, the Nitoprime 25IR will be absorbed very quickly leaving characteristic light coloured dry patches. It is recommended that a second priming coat is applied in these areas. While still wet, dress the surface with ½ kg/m² of Anti slip Grain No. 3 to provide a key for the application of Nitoflor TF5000. Ensure that the primer is touch dry prior to commencing application.

Mixing

It is important that Nitoflor TF5000 is mixed correctly. Pour the entire colour pack into the base container and mix for 15 - 30 seconds. Add the entire contents of the hardener into the mix and stir for further 30 seconds. Gradually empty the filler (aggregate) into the mix of base, colour pack and hardener and continue mechanical mixing, using a suitable Fosroc mixing paddle fitted to a slow speed forced action mixer, for a further 2 - 3 minutes, until all components are thoroughly blended.

Application

The mixed Nitoflor TF5000 should be spread to uniform thickness on the primed surface using either a garden rake or the edge of a plastic trowel. The material should be tamped with a wooden float to ensure complete compaction and finally finished to a closed even texture using a steel trowel. Screeding rods are useful to maintain a minimum compacted thickness of 5 mm.

Once mixed, the material must be used within the specified pot life (see under "Properties"). After this time, any unused material will have stiffened and should be discarded.



Nitoflor TF5000*

Expansion joints

Expansion joints in the existing substrate should be continued through the Nitoflor TF5000 topping, and filled to the required level with a suitable sealant from the Fosroc range incorporating appropriate movement accommodation factor (MAF).

Coving

Nitoflor TF5000 can be used to form a perimeter edge coving. Skilled applicators can also form stairs and nosings.

Sealing

Although Nitoflor TF5000 is impervious at 5 mm thick, in constantly wet operation areas or where a high degree of cleanliness is required, the Nitoflor TF5000 may be sealed with either Nitoflor FC130 or Nitoflor FC140. The Nitoflor TF5000 must have reached initial cure and high spots such as trowel marks rubbed down.

Cleaning

All tools and equipment should be cleaned with Fosroc Solvent 102* immediately after use.

Limitations

- Nitoflor TF5000 should not be applied on to surfaces which are known to or likely to suffer from rising damp or have a relative humidity greater than 75% as measured in accordance with BS 8023 Appendix A or by Hammond concrete/mortar moisture tester type COCO
- Fosroc does not recommend acid etching as a method of floor preparation. If used, the method should be approved by the project consultant
- Consult your local Fosroc technical department where application or service temperatures are outside the range of 5°C - 40°C
- Generally not suitable for external use, Contact local Fosroc office for further details

Estimating

Supply

Nitoflor TF5000	:	16.9 kg packs (including colour pack)
Anti slip Grain No. 3	:	20 kg bags
Nitoprime 25IR	:	1 & 3 kg packs
Fosroc Solvent 102	:	4 & 20 litre cans

Coverage

Nitoflor TF5000 : Approx. 10 kg/m² @ 5 mm thick.

Nitoprime 25IR : 3.5 – 4.3 m²/kg

Note: The above coverage rates are given for guidance only as actual quantities used will vary depending upon the nature of substrate and conditions on site.

Storage

Nitoflor TF5000 and Nitoprime 25IR have a shelf life of 12 months when stored in a dry place below 35°C in their original, unopened packs. Store under warehouse conditions below 35°C in the original, unopened packs. If stored at high temperature and/or high humidity conditions, the shelf life will be reduced.

Precautions

Health and safety

Nitoflor TF5000, Nitoprime 25IR and Fosroc Solvent 102 should not come in contact with skin and eyes or be swallowed. Avoid prolonged inhalation of solvent vapours. Some people are sensitive to epoxy resins, hardeners and solvents. Gloves, goggles and a barrier cream such as Kerodex Antisolvent or Rozalex Antipaint should be used. Ensure adequate ventilation and if working in enclosed areas use suitable breathing apparatus.

If mixed resin comes into contact with the skin, it must be removed before it hardens with a resin removing cream such as Kerocleanse Standard Grade Skin Cleanser or Rozaklens Industrial Skin Cleanser, followed by washing with soap and water. Do not use solvent. Fosroc Solvent 102 and should be washed from the skin immediately with soap and water.

Should accidental eye contamination occur with any of the above products, wash well with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately. Do not induce vomiting.

Fire

Nitoprime 25IR and Fosroc Solvent 102 are flammable. Do not expose to naked flames or other sources of ignition. No smoking during use. Containers should be tightly sealed when not in use. In the event of a fire, extinguish with a CO₂ or foam type extinguisher.

Flash points

Nitoprime 25IR : 39°C

Fosroc Solvent 102 : 33°C

Also refer to the Material Safety Data Sheet.



Nitoflor TF5000*

The Right Chemistry for Construction

Fosroc is one of the world's major manufacturers of advanced technology chemical based products for the construction and refurbishment industries. It operates internationally through a network of operating companies, licensees, distributors and agents.

Having over 70 years experience and using global resources for research and technical development, Fosroc has built a substantial worldwide reputation in manufacturing the most comprehensive range of high performance construction chemicals:

- Concrete admixtures
- Surface treatments
- Grouts and anchors
- Concrete repair
- Industrial flooring
- Protective coatings
- Joint sealants
- Waterproofing
- Adhesives
- F.R.P Structural Strengthening
- Specific building products

* Denotes the trademark of Fosroc International Ltd.

↑ See separate data sheet



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service.

Fars Iran Limited

No. 9, 25 th St., Khaled Eslamboli
(Vozara) Ave., Tehran 15139 - Iran

telephone:
+98 (21) 88719021

fax:
+98 (21) 88721664

email:
iran@fosroc.com

www.fosroc.com

