

Proofex 12*

Heavy duty self adhesive cross laminated bituminous waterproofing membrane

Uses

To provide a continuously bonded heavy duty waterproof membrane for building and civil engineering structures.

Advantages

- 2 mm thick (Nominal)
- Cold applied
- Fast application
- Uniform thickness of polymer bitumen membrane
- Good adhesion to primed concrete substrates
- Produces a continuous waterproof membrane system
- Cross laminated film for superior performance

Specification

The waterproofing membrane shall be a 2 mm thick self adhesive sheet membrane comprising of a polymer modified bitumen layer internally reinforced with polyester, bonded on to an outer surface of polyethylene film.

The polymer modified bitumen shall have an elongation in excess of 2000% when tested in accordance with ASTM D412.

Description

Proofex 12 is a cold applied self-adhesive sheet membrane comprising of a polymer modified bitumen layer internally reinforced with polyester, bonded on to an outer surface of polyethylene film.

The polymer bitumen adhesive layer is protected on the underside by a silicone release paper which is removed just prior to the application of Proofex 12 to the tack coat primed substrate.

The applied membrane is then immediately protected from UV light and from mechanical damage during subsequent back filling by the application of Protection Board, or a sand/cement screed.

Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Properties

Tensile strength (UEAtc)	: Long	680 N/5cm
	: Trans	625 N/5cm
Elongation of membrane (UEAtc)	: Long	43%
	: Trans	68%
Elongation of compound (ASTM D412)	: >	2000%
Tear resistance (UEAtc)	: Long	245 N/mm
	: Trans	243 N/mm
Adhesion to primed concrete (ASTM D1000)	: >	2.5 N/mm
Adhesion to self (ASTM D1000)	: >	2.1 N/mm
Chemical resistance (ASTM C543)	: >	Conforms

Instructions for use

Surface preparation

Concrete surfaces should be float finished and free from cavities and projecting nibs. All surfaces shall be dry and free from frost, surface laitence and contamination.

Priming

Proofex Tack Coat 6HT must be applied to the substrate and allowed to dry until it is tack free, prior to application of the membrane. All surfaces must be re-primed if left for more than 24 hours prior to the application of Proofex 12.

Application

Smooth transition should be made at wall/floor slab junctions using a sand/cement mortar and internal and external corners at walls and upstands pre-protected with Proofex Corner Pieces prior to the application of the membrane.

The membrane should be applied to the substrate having first removed the siliconized release paper, pressing the polyethylene film firmly ensuring that the adhesive bitumen compound bonds continuously to the substrate with no air pockets.

Allow at least a 75 mm edge and a 150 mm end lap. All laps should be rolled firmly to achieve a good seal. End laps should be staggered.

On vertical or inclined surfaces, the membrane shall be laid from the lowest level upwards. The membrane should be protected immediately after application in accordance with BS 8102:1990 by using Protection Board*†, or as appropriate with a sand/cement screed.

Proofex 12*

Proofex 12 and Proofex Engage

When used in conjunction with the Proofex Engage*† heavy duty waterproofing system, vertical surfaces are to be protected with two layers of Proofex 12 and Protection Board*†. The local Fosroc office will provide drawings for the joining detail between Proofex 12 & Proofex Engage*†.

Limitations

- Application temperature range: 5°C - 50°C
- For application below 15°C it may be necessary to slightly warm the back of the membrane to achieve an immediate bond
- In cold conditions, the membrane should be stored above 20°C prior to application to facilitate ease of application and immediate bond to the substrate

Estimating

Supply

Proofex 12 : 15 m long × 1 m wide roll

Proofex Tack Coat 6HT : 20 & 200 litre drums

Coverage

Proofex Tack Coat 6HT : 3 - 6 m² per litre

Storage

All products have a shelf life of 12 months if stored in a cool, dry store, away from sources of heat, in the original unopened packing. It should be stored horizontally, not more than one pallet high.

Precautions

Health and safety

There is no health hazards associated with the use of Proofex 12. If Proofex Tack Coat 6HT is swallowed, do not induce vomiting - drink a glass of water. If contact with eyes occurs, flood with copious amounts of clean water for at least 15 minutes and seek medical advice. If on the skin, remove any contaminated clothing and wash skin thoroughly. For further information, please consult Material Safety Data Sheets for the above products.

Fire

Proofex Tack Coat 6HT contains volatile, flammable solvents. Do not smoke in the presence of these products. Use only in ventilated areas, well away from any ignition source.

Flash point

Proofex Tack Coat 6HT : > 38°C

Additional information

Proofex 12 was formerly known as Proofex 12 X.



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Service.

Fars Iran Limited

No. 9, 25 th St., Khaled Eslamboli
(Vozara) Ave., Tehran 15139 - Iran

telephone:
+98 (21) 88719021

fax:
+98 (21) 88721664

email:
iran@fosroc.com

www.fosroc.com



Cert No. THR2004006